

BONDERITE M-CR 1001 AERO CHROMATE COATING (KNOWN AS ALODINE 1001)

Issued 9/29/2020

1. Introduction:

BONDERITE M-CR 1001 AERO (known as ALODINE 1001) is a nonflammable, chromic acid based, coating chemical that will produce a chrome conversion coating on aluminum and its alloys.

The coating formed by BONDERITE M-CR 1001 AERO is clear in color and it becomes a part of the aluminum surface. This chrome conversion coating offers the best affordable substrate for both paint adhesion and corrosion resistance.

BONDERITE M-CR 1001 AERO is used when it is desired to retain the silver white aluminum finish, either unpainted or with a clear finish over the chemical coating.

2. Operating Summary:

Spray Application:

For each 100 parts of bath, add 40 parts BONDERITE M-CR 1001 AERO to 60 parts of water.

Immersion Application:

For each 100 parts of bath, add 25 parts BONDERITE M-CR 1001 AERO to 75 parts of water.

Operation and Control:

Time

Spray	15 to 30 seconds
Immersion	2 to 5 minutes

Temperature

70° to 100° Fahrenheit

BONDERITE Titration

Spray	26.0 ml to 29.0 ml (0.38 – 0.42 oz/gal)
Immersion	16.0 ml to 18.0 ml (0.24 – 0.26 oz/gal)

3. The Process:

The process to prepare metal for painting normally consists of the following steps:

- A. Cleaning (BONDERITE C-IC 33 AERO)
- B. Water rinsing
- C. Apply BONDERITE M-CR 1001 AERO
- D. Water rinsing
- F. Drying



BONDERITE M-CR 1001 AERO CHROMATE COATING (KNOWN AS ALODINE 1001)

The process for polished aluminum where a minimal metal etch is desired normally consists of the following steps:

- A. Cleaning (BONDERITE C-IC 79 AERO)
- B. Water rinsing
- C. Apply BONDERITE M-CR 1001 AERO
- D. Water rinsing
- F. Drying

The work, after processing and drying, is ready to be painted.

4. Materials:

BONDERITE M-CR 1001 AERO (known as ALODINE 1001)
BONDERITE C-IC 33 AERO (known as TURCO ALUMIPREP 33), or
BONDERITE C-IC 79 AERO (known as METALPREP 79)

5. Equipment:

Acid resisting (rubber, stainless steel or plastic) buckets, troughs or other suitable containers should be used to hold the BONDERITE M-CR 1001 AERO or diluted BONDERITE M-CR 1001 AERO solution. Steel and galvanized containers should not be used. If production conditions warrant, troughs may be installed to collect the BONDERITE M-CR 1001 AERO coating chemical run-off for reuse.

Long handled, window type brushes, clean cloths or synthetic sponges may be used to brush on the BONDERITE M-CR 1001 AERO.

6. Surface Preparation:

Cleaning:

BONDERITE C-IC 33 AERO or BONDERITE C-IC 79 AERO are recommended for cleaning. A complete line of cleaners is available under the BONDERITE trademark and our representative will recommend the proper one for each installation.

BONDERITE C-IC 33 AERO is a phosphoric acid based cleaner which produces a chemically clean and corrosion free aluminum surface. Instructions for use of BONDERITE C-IC 33 AERO are found in its Technical Data Sheet.

BONDERITE C-IC 79 AERO is a multi-purpose phosphoric acid based cleaner, for most metals, which leaves the surface chemically clean and corrosion free. Instructions for use of BONDERITE C-IC 79 AERO are found in its Technical Data Sheet.

Water Rinsing:

After cleaning, the metal must be thoroughly rinsed with water. Inadequate rinsing may contaminate an BONDERITE M-CR 1001 AERO immersion bath or result in a surface condition which may cause corrosion of the finished part.

7. Applying BONDERITE M-CR 1001 AERO:

Buildup:

For spray application, BONDERITE M-CR 1001 AERO is diluted by mixing 40 parts of BONDERITE M-CR 1001 AERO and 60 parts of water for each 100 parts of bath volume required.



BONDERITE M-CR 1001 AERO CHROMATE COATING (KNOWN AS ALODINE 1001)

For immersion application, BONDERITE M-CR 1001 AERO is diluted by mixing 25 parts of BONDERITE M-CR 1001 AERO and 75 parts of water for each 100 parts of bath volume required.

NOTE: Operators should be equipped with rubber gloves, aprons, and goggles to avoid contact with the solution. Adequate ventilation should be provided.

BONDERITE M-CR 1001 AERO coating chemical should not be allowed to dry on the metal surface. With spray application the surface should be rewet with fresh BONDERITE M-CR 1001 AERO several times during the treatment time. If drying does occur, rewet with BONDERITE M-CR 1001 AERO coating solution prior to water rinsing.

Selecting the size of the area to be treated at one time depends on the method of application, condition of the metal surface, method in which the surface was cleaned, temperature and part configuration.

Powdering of a chrome conversion coating can result from poor cleaning, drying, over reacting, or for other reasons. Powder can affect paint adhesion. Gently wipe and remove the powder, without abrading the chemical coating, with a dry, clean rag after the work has dried. Caution should be taken not to redeposit oils, lint, or other soils back on the aluminum surface.

8. TESTING AND CONTROL:

BONDERITE Titration:

Pour a 50 ml sample of the BONDERITE M-CR 1001 AERO bath (immersion/spray) into an iodometric flask and dilute with water to approximately 100 ml. Add approximately 1 gram (1/2 teaspoon) of Reagent 2 (Potassium Iodide) and agitate the solution until the solid material is completely dissolved. Add approximately 10 ml of Reagent Solution 49 (C.P. HCl) in 5 ml increments to the lip of the flask, raising the stopper slightly after each addition to allow the acid to run into the flask. Rinse the lip several times with water and replace the stopper.

Allow the sample to settle for approximately one minute, titrate with Titrating Solution 104 (0.1N Na₂S₂O₃) until a **straw** color is obtained. Do Not re-zero the burette. Add several milliliters of Indicator 10 (soluble starch solution) to the sample. The solution should turn blue-black. Continue to titrate with Titrating Solution 104 (0.1N Na₂S₂O₃) until the **blue-black** color disappears.

Record the number of milliliters of Titrating Solution 104 as the BONDERITE titration.

9. After Treatment:

Water Rinsing:

A thorough rinse with clean water is necessary to remove residual BONDERITE M-CR 1001 AERO coating chemical salts from the metal surface. Blistering and corrosion problems under paint are often the results of poor rinsing. Chemical salts trapped under a paint film will eventually result in blistering or corrosion problems.

Drying:

As an aid to drying, heating the treated part, blowing off with clean, dry, filtered, low pressure forced air, or gently wiping with a dry, clean rag will lessen the time required. Do not allow the aluminum metal temperature to exceed 140 Fahrenheit.

Paint soon after the work is dry in order to prevent soils or oxidation from re-contaminating the prepared metal surface.



BONDERITE M-CR 1001 AERO CHROMATE COATING (KNOWN AS ALODINE 1001)

10. Storage Requirements:

BONDERITE M-CR 1001 AERO coating chemical will freeze at 32° Fahrenheit. It is recommended that the product be stored where freezing will not occur. However, should it freeze, simply thaw it in a warm place and stir it prior to use.

11. Waste Disposal Information:

Applicable regulations concerning disposal and discharge of chemicals should be consulted and followed.

Disposal information for the chemical products used in this process is given on the Safety Data Sheet for each product.

The processing bath is acidic and contains hexavalent chromium. Waste treatment and neutralization may be required prior to discharge to sewer.

12. Precaution:

Consult the appropriate Safety Data Sheets for safety and handling guidelines for the products listed in this bulletin.

NOTICE:

The above information and recommendations concerning this product are based upon our laboratory tests and field use experience. However, since conditions of actual use are beyond our control, any recommendations or suggestions are made without warranty, express or implied. Manufacturer's and seller's sole obligation shall be to replace that portion of the product shown to be defective. Neither shall be liable for any loss, damage, or injury, direct or consequential, arising out of the use of this product.

Henkel Corporation | 32100 Stephenson Highway | Madison Heights, MI 48071 PHONE: (248) 583-9300 | FAX: (248) 583-2976 | www.henkelna.com/

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

