

**BONDERITE S-ST 5351 AERO  
PAINT STRIPPER  
(KNOWN AS TURCO 5351/T-5469)**

Issued 9/23/2016

**INTRODUCTION:**

BONDERITE S-ST 5351 AERO (known as TURCO 5351/T-5469) is a yellow, viscous paint remover developed to remove epoxy, polyurethane and similar coatings from metal surfaces at ambient temperatures.

BONDERITE S-ST 5351 AERO clings to vertical and overhead surfaces and forms a surface film that helps retard evaporation and extend the working life of the stripper. BONDERITE S-ST 5351 AERO should not be used on material that are affected by chlorinated hydrocarbons.

**FEATURES:**

- Nonflammable
- Used as received, No mixing or dilution required
- Applied by nonatomizing spray, brushing or flow-on methods
- Rinsed from surfaces by high pressure cold water
- Can be used on high strength steel
- Chemically neutral

**CORROSION DATA:**

One by two inch panels, fabricated from the below listed metals, were immersed in BONDERITE S-ST 5351 AERO for 7 days @ 40°C. Weight changes in mg, per panel were as follows:

Magnesium	0.1 mg	2024 Bare Aluminum	0.1 mg
1100 Aluminum	-0.1 mg	Cadmium Plated	-0.1 mg
1020 Steel	0.1 mg	2024 Alclad	-0.4 mg
Tin	-0.1 mg	7075 Bare Aluminum	-0.4 mg
Dow #7	0.0 mg	7075 Alclad	-0.7 mg

**USE INSTRUCTIONS:**

Apply a thick coating by means of a nonatomizing spray or by brushing. Allow sufficient time for remover to thoroughly loosen paint. When paint is loose, agitate all areas with a stiff bristle brush to insure complete removal of all paint.

Rinse BONDERITE S-ST 5351 AERO and paint residue with high pressure, high volume water or with steam. Slight brushing during rinsing aids in complete removal of all residues.

**DISPOSAL INFORMATION:**

Dispose of remover and paint residue per local state and regional regulations. Refer to your HENKEL SURFACE TECHNOLOGIES MATERIAL SAFETY DATA SHEET for additional disposal information.



**BONDERITE S-ST 5351 AERO  
PAINT STRIPPER  
(KNOWN AS TURCO 5351/T-5469)**

---

**PRECAUTIONARY INFORMATION:**

**DANGER! POISON! Rapidly absorbed through skin. Causes severe burns. Harmful or fatal if swallowed. Prolonged exposure to high concentrations of vapor may cause irritation to eyes and respiratory tract.**

BONDERITE S-ST 5351 AERO contains methylene chloride, phenol and sodium chromate. Avoid contact with eyes, skin and clothing. Do not take internally. Use with adequate (equivalent to outdoor) ventilation. Avoid breathing vapors.

Protective clothing, such as a chemical face shield or goggles, gloves, boots and apron, made from solvent-resistant materials, should be worn when handling this product.

Do not use BONDERITE S-ST 5351 AERO near welding arcs, torches and open flames since hazardous gases may be formed.

Containers exposed to moderate heat, above 32°C (90°F) may develop sufficient internal pressure to rupture. Use care in opening containers to avoid spurting of contents.

Before using this product refer to container label and HENKEL SURFACE TECHNOLOGIES MATERIAL SAFETY DATA SHEET for additional precautionary, handling and first aid information.

**NOTICE:**

**The above information and recommendations concerning this product are based upon our laboratory tests and field use experience with this or similar products. However, since conditions of actual use are beyond our control, any recommendations or suggestions are made without warranty, express or implied. Manufacturer's and seller's sole obligation shall be to replace that portion of the product shown to be defective. Neither shall be liable for any loss, damage or injury, direct or consequential, arising out of the use of this product.**

---

Henkel Corporation | 32100 Stephenson Highway | Madison Heights, MI 48071  
PHONE: (248) 583-9300 | FAX: (248) 583-2976 | [www.henkelna.com/](http://www.henkelna.com/)

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.**

The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

