

TECHNOMELT® SUPRA 126

February 2024

Product description

TECHNOMELT® SUPRA 126 provides the following product characteristics:

Technology	Hot Melt adhesive
Application	Packaging Industry
Appearance	Pale yellow, solid

Application areas

TECHNOMELT® SUPRA 126 is a high-quality food packaging hot melt adhesive for case, carton, and tray formation.

Product properties

- Great heat stability with excellent molten clarity
- Low odor
- Fast setting
- High hot tack
- Great adhesion on a variety of common case, carton, and tray substrates at a range of temperatures
- Excellent adhesion in freezer temperatures
- High heat resistance

Technical data

TECHNOMELT® SUPRA 126:

Solids content, %	100
Viscosity, Brookfield - 350°F, mPa.s (cP)	977 - 1300
Density, lbs/gal	7.15
Softening point, °F	229

Compliance with food packaging regulations

TECHNOMELT® SUPRA 126 conforms to the FDA regulation CFR 21 175.105 for indirect food contact.

The responsibility for compliance with the specific conditions is with the converter and not with the adhesive supplier.

A food contact statement with further details is available upon request.

Directions for use

Preliminary statement:

Prior to use it is necessary to read the **Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed. Please also refer to the local safety instructions and contact Henkel for analytical support.

Working temperature

Recommended working temperature: 325 to 375°F.

The recommended application temperature is 350°F, however the specific application requirements may require customization.

It is not recommended to go beyond the running temperature range. Bond quality and processing can be affected by application temperature.

Handling information

Due to the variety of substrates available, adhesion of materials can be very different. Therefore pre-tests should be carried out. See also "General Instructions for the Application of Hotmelts". Material is applied hot. Appropriate clothing and eye protection should be used. Adequate ventilation is recommended when using this product. Refer to Safety Data Sheet.

Storage

Rotate stock using oldest material first. Do not mix with other adhesives. When stored in a dry and cool place in the original unopened containers, shelf life is as follows.

Shelf life

Shelf-life (in unopened original packaging), months 24

Classification:

Please refer to the corresponding **Safety Data Sheet** for details on:

Hazardous Information

Transport Regulations

Safety Regulations

Additional information

Disclaimer

The information provided in this Technical data sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical data sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1